



High Standards. Higher Performance. Highest Temperatures.

Dynaglas-DynaPleat from Filtration Specialties, Inc.

Media Efficiency* by Particle Size
(Initial % Collection without pulsing)

MEDIA	Particle Size Range (microns) (in. w.c.)								Initial DP
	.3-.5	.5-1	1-2	2-3	3-4	4-5	5-6	6+	
1702	17.30	35.20	61.60	90.75	98.01	98.93	99.00	99.60	0.5
1702P	41.77	44.76	70.73	94.19	98.60	99.32	99.25	99.60	0.65
1704	40.72	64.02	84.92	97.49	99.48	99.71	99.70	99.80	0.7
1702HT	26.90	51.68	81.81	97.61	99.21	99.63	99.90	99.90	1.4
1105D	29.23	52.58	75.31	94.43	98.79	99.46	99.60	99.40	0.5
1405D	23.53	43.90	66.13	90.10	98.00	99.06	99.20	99.40	0.4
2250P	21.45	33.77	53.05	82.68	96.28	98.14	98.60	98.80	0.4
2201	27.60	48.34	64.11	75.24	89.22	94.02	96.96	98.37	0.5

Data compiled by independent laboratory

Media	Finish	Continuous Temp.	Surge Temp.
Dynaglas 1702 & 2201	Unfinished	700°F (371°C)	750°F (399°C)
Dynaglas 1704, 1105D, 1405D	Proprietary Silicone-based	550°F (288°C)	600°F (316°C)
Dynaglas 1702HT	HT Proprietary	800°F (427°C)	1000°F (538°C)
DynaPleat 1702P, 2250P	Pleatable Phenolic-based	425°F (218°C)	650°F (343°C)

* Test Conditions	
Fluid:	Air
Face Velocity:	30 fpm (0.152 meters/sec)
Temperature:	Ambient
Contaminant:	ISO Fine Test Dust, neutralized
Samples	Flat sheet media, single layer

High Temperature Fiber Materials

+1-757-363-9818
+1-917-464-9889
Sales@HighTempFelt.com

Voice
Fax
Email

<http://www.HighTempFelt.com>